Accredited for compliance with ISO/IEC 17025 – Testing

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration and inspection reports

Accreditation No. 2735

DRY FLOOR FRICTION SLIP RESISTANCE TEST

Fosroc Nitoflor FC150 HP/SL + Fosroc Nitoflor Anti-Slip Grains 01 Silica Sand 16/30# + Fosroc Nitoflor PA

Prepared for:	Fosroc Max Elias 7 Lucca Road WYONG NSW 2259
Sample Description:	Fosroc Nitoflor FC150 HP/SL + Fosroc Nitoflor Anti-Slip Grains 01 Silica Sand 16/30# + Fosroc Nitoflor PA
No. of Specimens & Size Supplied:	1 off , 500x1000 mm, (Sampling Conducted by Client)
Specimen Preparation:	Washed with water and pH neutral detergent, rinsed then dried.
Test Condition & Slope:	Unfixed, N/A
Test Direction:	Test direction not applicable.
Air Temperature:	23°C
Test Standard:	AS 4586:2013 Slip resistance classification of new pedestrian surface materials, Appendix B - Dry Floor Friction Test
Test Location:	ATTAR 44-48 Rocco Drive, Scoresby, VIC, 3179
Test Date:	30 July 2024
Test Equipment:	Tortus Floor Friction Tester Mk III, Serial Number 318
Slider Rubber:	Slider 96 Batch No. #27 prepared on P400 SiC paper.
Test Personnel:	Louie Karkatzoulis

Coefficient of Friction (COF):	**Run 1**	**Run 2**
	0.96	0.91
Mean COF (rounded to 0.05)	**0.95**	
Classification:	**D1**	

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance procedures and wear on their slip resistance be checked.

Prepared by:



Louie Karkatzoulis
Compliance and Testing Technician

Reviewed By:



Daniel King BSc/BEng (mat) Hons., MIEAust
General Manager - Compliance Services
Approved Signatory

This report may not be reproduced except in its entirety.

www.attar.com.au
ABN: 14 006 554 785

Engineering Materials Evaluation Pty Ltd t/a ATTAR
44-48 Rocco Drive, Scoresby VIC 3179

Ph: 1300 139 155
E: admin@attar.com.au



Figure 1: Fosroc Nitoflor FC150 HP/SL + Fosroc Nitoflor Anti-Slip Grains 01 Silica Sand 16/30# + Fosroc Nitoflor PA

This report may not be reproduced except in its entirety.

CLASSIFICATION CRITERIA – AS 4586: 2013
Dry Floor Friction Test - Appendix B

Slip resistance

The 'dry floor friction' test method in Appendix B is not suitable for heavily profiled surfaces or carpets.

Compliance

The surface shall comply with the stated classification for the test method that is nominated and declared by the manufacturer or supplier.

TABLE 3: CLASSIFICATION OF PEDESTRIAN SURFACE MATERIALS ACCORDING TO THE AS 4586 DRY FLOOR FRICTION TEST

Classification	Floor friction tester mean value
D1	≥0.40
D0	<0.40

Means of demonstrating compliance

Pedestrian surfaces that are classified in accordance with Table 3 where appropriate, shall meet the following criteria:

(a) The mean test results shall be as follows:

(i) For Classification D1 in Table 3—
(A) the mean of the test results shall be equal to or greater than 0.4; and
(B) each individual slope corrected result shall be equal to or greater than 0.35.

If either of these criteria is not met, the lot shall be considered to be Classification D0.

(b) The classification in accordance with Table 3 shall be determined by—

(i) selecting and testing specimens at random as specified in Appendix B of AS4586; or

(ii) carrying out continuous testing and process control in accordance with AS 3942.

(c) When testing individual lots, if a particular test fails to produce the expected classification it shall be permissible to—

(i) disregard the first sample, resample a minimum of 10 specimens from the whole lot, retest and apply the criteria to the new sample; or

(ii) subdivide the lot into smaller lots of different quality, resample, retest and reclassify each of the smaller lots.

This report may not be reproduced except in its entirety.